



**PLEASURE BOATS
WITHOUT FILLER**



DATA
N°31

APPLICATIONS

PRODUCTS

<p>PU 320 or PU 99 or PU 77</p> <ul style="list-style-type: none"> • 2 to 3 crossed coats of 40 dry microns • Theoretical spreading rate : PU 320 = 4,6 Sq.m/L for 80 dry microns (depends on color) PU 99 = 6,6 Sq.m/L for 80 dry microns (depends on color) PU 77 = 6,5 Sq.m/L for 80 dry microns (depends on color) 	<p>PU 230 or PU 99 or PU 77</p>	<p>FLEXIBLE POLYURETHANE ACRYLIC LACQUER E¹ → TOPCOAT COLOR PU 320 or POLYESTER-POLYURETHANE LACQUER E² → POLYTOP PU 99 or ACRYLIC-POLYURETHANE LACQUER E³ → POLYTOP PU 77</p>
<ul style="list-style-type: none"> • 1 coat of 25 to 35 dry microns • Theoretical spreading rate : 14,9 Sq.m/L for 35 dry microns 	<p>EPU 221</p>	<p>FLEXIBLE INTERCOAT EPOXY-URETHANE D → INTERFACE EPU 221</p>
<ul style="list-style-type: none"> • 2 coats of 120 dry microns • Theoretical spreading rate : EP 213 HB = 4,8 Sq.m/L for 120 dry microns EP 215 HB = 4,2 Sq.m/L for 120 dry microns 	<p>EP 213 or 215 HB</p>	<p>UNDERCOAT EPOXY PAINT C → UNDERCOAT EP 213 or 215 HB</p>
<ul style="list-style-type: none"> • 1 coat of 60 dry microns • Theoretical spreading rate : 8,3 Sq.m/L for 60 dry microns 	<p>EP 211</p>	<p>PRIMAIRE EPOXY ANTICORROSION B → EPOXY PRIMER EP 211</p>
<p>Metal cleaner treatment : spraying/rinsing/drying</p>		<p>A → METAL CLEANER or BLASTING SA 2- 1/2, SA 3</p>
<p>Metal cleaner treatment : spraying/rinsing/drying</p>		<p>A → METAL CLEANER or BLASTING SA 2- 1/2, SA 3</p>
<ul style="list-style-type: none"> • 1 coat of 60 dry microns • Theoretical spreading rate : 8,3 Sq.m/L for 60 dry microns 	<p>EP 211</p>	<p>PRIMAIRE EPOXY ANTICORROSION B → EPOXY PRIMER EP 211</p>
<ul style="list-style-type: none"> • 3 coats of 120 dry microns • Theoretical spreading rate : EP 213 HB = 4,8 Sq.m/L for 120 dry microns EP 215 HB = 4,2 Sq.m/L for 120 dry microns 	<p>EP 213 or 215 HB</p>	<p>UNDERCOAT EPOXY PAINT C → UNDERCOAT EP 213 or 215 HB</p>
<ul style="list-style-type: none"> • 1 coat of 75 dry microns • Theoretical spreading rate : 5 Sq.m/L for 75 dry microns 	<p>MPO 500</p>	<p>INTERCOAT VYNILIC PITCH [single component] D → UNDERCOAT MPO 500</p>
<ul style="list-style-type: none"> • 2 to 3 coats of 75 dry microns • Theoretical spreading rate : 5 Sq.m/L for 75 dry microns 		<p>ANTIFOULING E → ISIS : ablative matrix antifouling paint</p>

* ALL OUR INFORMATION IS INDICATIVE AND NONCONTRACTUAL