

RACE BOATS

DATA N°11



APPLICATIONS

PRODUCTS

<ul style="list-style-type: none"> <li>• 2 to 3 crossed coats of 35 to 40 dry microns</li> <li>• Theoretical spreading rate : 4,9 to 4,3 Sq.m/L for 70 to 80 dry microns</li> </ul>		<p><b>FLEXIBLE ACRYLIC POLYURETHANE VARNISH</b>            F → TOPCOAT CLEAR PU 360 UVR <b>OPTION</b></p>
<ul style="list-style-type: none"> <li>• 2 to 3 crossed coats of 35 to 40 dry microns</li> <li>• Theoretical spreading rate : 5,3 to 4,6 Sq.m/L for 70 to 80 dry microns [depends color]</li> </ul>		<p><b>FLEXIBLE ACRYLIC POLYURETHANE LACQUER</b>            E → TOPCOAT COLOR PU 320</p>
<ul style="list-style-type: none"> <li>• 1 coat of 25 µm secs</li> <li>• Theoretical spreading rate : 20,8 Sq.m/L for 25 dry microns</li> </ul>		<p><b>FLEXIBLE INTERCOAT EPOXY-URETHANE</b>            D → INTERFACE EPU 221</p>
<ul style="list-style-type: none"> <li>• 1 to 2 coats of 120 dry microns</li> <li>• Theoretical spreading rate :                EP 213 HB = 4,8 Sq.m/L for 120 dry microns                EP 215 HB = 4,2 Sq.m/L for 120 dry microns</li> </ul>		<p><b>UNDERCOAT EPOXY PAINT</b>            C → UNDERCOAT EP 213 or 215 HB</p>
<p>Practical spreading rate : 1l/Sq.m/mm of thickness</p>		<p><b>SOLVENT FREE EPOXY FILLER</b>            B → MIX FILL 100 and/or MIX FILL 300</p>
		<p>A → GELCOAT MUST BE SAND WITH GRIT 80/120</p>
		<p>A → GELCOAT MUST BE SAND WITH GRIT 80/120</p>
<p>Practical spreading rate : 1l/Sq.m/mm of thickness</p>		<p><b>SOLVENT FREE EPOXY FILLER</b>            B → MIX FILL 100 and/or MIX FILL 300</p>
<ul style="list-style-type: none"> <li>• 2 coats of 120 dry microns</li> <li>• Theoretical spreading rate :                EP 213 HB = 4,8 Sq.m/L for 120 dry microns                EP 215 HB = 4,2 Sq.m/L for 120 dry microns</li> </ul>		<p><b>UNDERCOAT EPOXY PAINT</b>            C → UNDERCOAT EP 213 or 215 HB</p>
<ul style="list-style-type: none"> <li>• 2 to 3 coats of 75 dry microns</li> <li>• Theoretical spreading rate : 5 Sq.m/L for 75 dry microns</li> </ul>		<p><b>ANTIFOULING</b>            D → GYPTIS : hard matrix antifouling paint            PROTIS : ablative matrix antifouling paint</p>

\* ALL OUR INFORMATION IS INDICATIVE AND NONCONTRACTUAL