

REPAIR
TREATMENT

DATA
N°60



APPLICATIONS

PRODUCTS

	↓	↑	
<ul style="list-style-type: none"> • 2 to 3 coats of 150 dry microns • Theoretical spreading rate : 150 to 200 gr per coat 	Below waterline		<p>A → On laminate, after removal of gelcoat (grinding or sandblasting)</p> <p>SOLVENT FREE EPOXY FILLER B → SR 1610 / SD 2613 standard SD 2612 tropical</p>
<p>Practical spreading rate : 1l/Sq.m/mm of thickness</p>		100	<p>SOLVENT FREE EPOXY FILLER C → MIX FILL 100 et/ou MIX FILL 300</p>
<p>EPOXYGUARD 455 :</p> <ul style="list-style-type: none"> • 1 to 2 coats of 300 dry microns • Theoretical spreading rate : 3,3 Sq.m of 300 dry microns <p>EP 213 ou 215 HB :</p> <ul style="list-style-type: none"> • 1 coat of 120 to 130 dry microns • Theoretical spreading rate : EP 213 HB : 4,4 Sq.m of 130 dry microns EP 215 HB : 3,8 Sq.m of 130 dry microns <p>or</p> <p>UNDERCOAT EP 213 or 215 HB :</p> <ul style="list-style-type: none"> • 3 coats of 120 dry microns • Theoretical spreading rate : EP 213 HB = 4,8 Sq.m of 120 dry microns EP 215 HB = 4,2 Sq.m of 120 dry microns 	455	<p>UNDERCOAT EPOXY PAINT D¹ → EPOXYGUARD 455 + UNDERCOAT EP 213 or 215 HB</p> <p>or</p> <p>D² → UNDERCOAT EP 213 or 215 HB</p>	
	EP 213 or 215 HB		300
<ul style="list-style-type: none"> • 1 coat of 75 dry microns • Theoretical spreading rate : 5 Sq.m/L for 75 dry microns 		MPO 500	<p>INTERCOAT VYNILIC PITCH (single component) E → UNDERCOAT MPO 500</p>
<ul style="list-style-type: none"> • 2 to 3 coats of 75 dry microns • Theoretical spreading rate : 5 Sq.m/L for 75 dry microns 			<p>ANTIFOULING G → GYPTIS : hard matrix antifouling paint PROTIS : ablative matrix antifouling paint</p>

* ALL OUR INFORMATION IS INDICATIVE AND NONCONTRACTUAL