



**PROTECT
TREATMENT**



DATA
N°61

APPLICATIONS

PRODUCTS

<ul style="list-style-type: none"> • 3 coats of 100 to 120 dry microns • Theoretical spreading rate : EP 213 HB = 4,8 Sq.m of 120 dry microns EP 215 HB = 4,2 Sq.m of 120 dry microns 	<p style="writing-mode: vertical-rl; transform: rotate(180deg);">Below waterline</p> <p style="text-align: center;">EP 213 or 215 HB</p>	<p>A → On gelcoat sand with 120 orbital grit</p> <p>UNDERCOAT EPOXY PAINT B → UNDERCOAT EP 213 or 215 HB</p>
<ul style="list-style-type: none"> • 1 coat of 75 dry microns • Theoretical spreading rate : 5 Sq.m/L for 75 dry microns 	<p style="text-align: center;">MPO 500</p>	<p>INTERCOAT VYNILIC PITCH (single component) E → UNDERCOAT MPO 500</p>
<ul style="list-style-type: none"> • 2 to 3 coats of 75 dry microns • Theoretical spreading rate : 5 Sq.m/L for 75 dry microns 		<p>ANTIFOULING G → GYPTIS : hard matrix antifouling paint PROTIS : ablative matrix antifouling paint</p>