

WASTE WATER

DATA N°49



APPLICATIONS

PRODUCTS

<ul style="list-style-type: none"> • minimum 2 coats of 300 dry microns → (3 coats recommended) • Theoretical spreading rate : 3,2 Sq.m/L for 300 dry microns 		<p>EPOXY FINISHING WITHOUT VOLATILE ELEMENT C → EPOXYGUARD 455</p> <p>Roller or AIRLESS application</p>
<p>ON STEEL :</p> <ul style="list-style-type: none"> • 1 coat of 60 dry microns • Theoretical spreading rate : 8,3 Sq.m/L for 60 dry microns <p>ON ALUMINIUM :</p> <ul style="list-style-type: none"> • 1 coat of 40 dry microns • Theoretical spreading rate : 12,5 Sq.m/L for 40 dry microns 	<p style="text-align: center;">455</p> <p style="text-align: center;">EP 211</p>	<p>ANTICORROSIVE EPOXY PRIMER B → EPOXY PRIMER EP 211</p> <p>Roller or AIRLESS application</p>
<p style="text-align: center;">ON STEEL</p>		<p>A → BLASTING TO SWEDISH STANDARD SA 2,5/SA 3</p>
<p>ON STEEL :</p> <ul style="list-style-type: none"> • 1 coat of 60 dry microns • Theoretical spreading rate : 8,3 Sq.m/L for 60 dry microns <p>ON ALUMINIUM :</p> <ul style="list-style-type: none"> • 1 coat of 40 dry microns • Theoretical spreading rate : 12,5 Sq.m/L for 40 dry microns 	<p style="text-align: center;">EP 211</p>	<p>ANTICORROSIVE EPOXY PRIMER B → EPOXY PRIMER EP 211</p> <p>Roller or AIRLESS application</p>
<ul style="list-style-type: none"> • 1 coat of 100 to 120 dry microns • Theoretical spreading rate : 4,8 Sq.m/L for 120 dry microns 	<p style="text-align: center;">EP 213 HB</p>	<p>UNDERCOAT EPOXY C → UNDERCOAT EP 213 HB</p> <p>Roller or AIRLESS application</p>
<ul style="list-style-type: none"> • 1 coat of 60 to 70 dry microns • Theoretical spreading rate : 7,4 Sq.m/L for 70 dry microns 	<p style="text-align: center;">PU 77</p>	<p>POLYURETHANE ACRYLIC LACQUER D → ACRYLTOP PU 77 Color RAL or AFNOR</p> <p>Roller or AIRLESS application</p>

* ALL OUR INFORMATION IS INDICATIVE AND NONCONTRACTUAL