

**DRINKING WATER**



DATA N°51

**APPLICATIONS**

**PRODUCTS**

<ul style="list-style-type: none"> <li>• minimum 2 coats of 300 dry microns → (3 coats recommended)</li> <li>• Theoretical spreading rate : 3,3 Sq.m/L for 300 dry microns</li> </ul>	BIOTANK	<p><b>FREE SOLENT EPOXY ALIMENTARY FINISHING</b> C → BIOTANK</p> <p>Only roller application</p>
<ul style="list-style-type: none"> <li>• 1 to 2 coats of 100 to 120 dry microns</li> <li>• Theoretical spreading rate : EP 213 HB : 4,8 Sq.m/L for 120 dry microns EP 215 HB : 4,2 Sq.m/L for 120 dry microns</li> </ul>	EP 213 or 215 HB	<p><b>UNDERCOAT EPOXY PAINT</b> C → UNDERCOAT EP 213 or 215 HB</p>
<p>Practical spreading rate : 1l/Sq.m/mm of thickness</p>		<p><b>SOLVENT FREE EPOXY FILLER</b> B → MIX FILL 100 <b>OPTION</b></p>
<ul style="list-style-type: none"> <li>• 1 coat of 120 to 130 dry microns</li> <li>• Theoretical spreading rate : EP 213 HB : 4,4 Sq.m/L for 130 dry microns EP 215 HB : 3,8 Sq.m/L for 130 dry microns</li> </ul>	EP 213 or 215 HB	<p><b>UNDERCOAT EPOXY PAINT</b> C → UNDERCOAT EP 213 or 215 HB</p>
<ul style="list-style-type: none"> <li>• 1 coat of 120 to 130 dry microns</li> <li>• Theoretical spreading rate : EP 213 HB : 4,4 Sq.m/L for 130 dry microns EP 215 HB : 3,8 Sq.m/L for 130 dry microns</li> </ul>	EP 213 or 215 HB	<p><b>UNDERCOAT EPOXY PAINT</b> C → UNDERCOAT EP 213 or 215 HB</p>
<p>Practical spreading rate : 1l/Sq.m/mm of thickness</p>		<p><b>SOLVENT FREE EPOXY FILLER</b> B → MIX FILL 100 <b>OPTION</b></p>
<ul style="list-style-type: none"> <li>• 1 to 2 coats of 100 to 120 dry microns</li> <li>• Theoretical spreading rate : EP 213 HB : 4,8 Sq.m/L for 120 dry microns EP 215 HB : 4,2 Sq.m/L for 120 dry microns</li> </ul>	EP 213 or 215 HB	<p><b>UNDERCOAT EPOXY PAINT</b> C → UNDERCOAT EP 213 or 215 HB</p>
<ul style="list-style-type: none"> <li>• 1 coat of 60 to 70 dry microns</li> <li>• Theoretical spreading rate : 7,4 Sq.m/L for 70 dry microns</li> </ul>	PU 77	<p><b>POLYURETHANE ACRYLIC LACQUER</b> D → ACRYLTOP PU 77 Color RAL or AFNOR Roller or AIRLESS application</p>

\* ALL OUR INFORMATION IS INDICATIVE AND NONCONTRACTUAL