

WASTE WATER



DATA N°52

APPLICATIONS

PRODUCTS

| | | |
|---|------------------|---|
| <ul style="list-style-type: none"> • minimum 2 coats of 300 dry microns → (3 coats recommended) • Theoretical spreading rate : 3,3 Sq.m/L for 300 dry microns | 455 | <p>EPOXY FINISHING WITHOUT VOLATILE ELEMENT C → EPOXYGUARD 455</p> <p>Roller or AIRLESS application</p> |
| <ul style="list-style-type: none"> • 1 to 2 coats of 100 to120 dry microns • Theoretical spreading rate : EP 213 HB : 4,8 Sq.m/L for 120 dry microns EP 215 HB : 4,2 Sq.m/L for 120 dry microns | EP 213 or 215 HB | <p>UNDERCOAT EPOXY PAINT C → UNDERCOAT EP 213 or 215 HB</p> |
| <p>Practical spreading rate : 1l/Sq.m/mm of thickness</p> | | <p>SOLVENT FREE EPOXY FILLER B → MIX FILL 100 OPTION</p> |
| <ul style="list-style-type: none"> • 1 coat of 120 to130 dry microns • Theoretical spreading rate : EP 213 HB : 4,4 Sq.m/L for 130 dry microns EP 215 HB : 3,8 Sq.m/L for 130 dry microns | EP 213 or 215 HB | <p>UNDERCOAT EPOXY PAINT C → UNDERCOAT EP 213 or 215 HB</p> |
| <ul style="list-style-type: none"> • 1 coat of 120 to130 dry microns • Theoretical spreading rate : EP 213 HB : 4,4 Sq.m/L for 130 dry microns EP 215 HB : 3,8 Sq.m/L for 130 dry microns | EP 213 or 215 HB | <p>UNDERCOAT EPOXY PAINT C → UNDERCOAT EP 213 or 215 HB</p> |
| <p>Practical spreading rate : 1l/Sq.m/mm of thickness</p> | | <p>SOLVENT FREE EPOXY FILLER B → MIX FILL 100 OPTION</p> |
| <ul style="list-style-type: none"> • 1 to 2 coats of 100 to120 dry microns • Theoretical spreading rate : EP 213 HB : 4,8 Sq.m/L for 120 dry microns EP 215 HB : 4,2 Sq.m/L for 120 dry microns | EP 213 or 215 HB | <p>UNDERCOAT EPOXY PAINT C → UNDERCOAT EP 213 or 215 HB</p> |
| <ul style="list-style-type: none"> • 1 coat of 60 to 70 dry microns • Theoretical spreading rate : 7,4 Sq.m/L for 70 dry microns | PU 77 | <p>POLYURETHANE ACRYLIC LACQUER D → ACRYLTOP PU 77 Color RAL or AFNOR Roller or AIRLESS application</p> |

* ALL OUR INFORMATION IS INDICATIVE AND NONCONTRACTUAL