

FUEL



DATA N°53

APPLICATIONS

PRODUCTS

<ul style="list-style-type: none"> • minimum 3 coats of 300 dry microns • Theoretical spreading rate : 3,3 Sq.m/L for 300 dry microns 	<p>FUELTANK</p>	<p>FREE SOLVENT EPOXY POLYAMINE FOR FUEL STORAGE C → FUELTANK</p> <p>Roller application or airless application</p>
<ul style="list-style-type: none"> • 1 to 2 coats of 100 to 120 dry microns • Theoretical spreading rate : EP 213 HB : 4,8 Sq.m/L for 120 dry microns EP 215 HB : 4,2 Sq.m/L for 120 dry microns 	<p>EP 213 or 215 HB</p>	<p>UNDERCOAT EPOXY PAINT C → UNDERCOAT EP 213 or 215 HB</p>
<p>Practical spreading rate : 1l/Sq.m/mm of thickness</p>		<p>SOLVENT FREE EPOXY FILLER B → MIX FILL 100 OPTION</p>
<ul style="list-style-type: none"> • 1 coat of 120 to 130 dry microns • Theoretical spreading rate : EP 213 HB : 4,4 Sq.m/L for 130 dry microns EP 215 HB : 3,8 Sq.m/L for 130 dry microns 	<p>EP 213 or 215 HB</p>	<p>UNDERCOAT EPOXY PAINT C → UNDERCOAT EP 213 or 215 HB</p>
<ul style="list-style-type: none"> • 1 coat of 120 to 130 dry microns • Theoretical spreading rate : EP 213 HB : 4,4 Sq.m/L for 130 dry microns EP 215 HB : 3,8 Sq.m/L for 130 dry microns 	<p>EP 213 or 215 HB</p>	<p>UNDERCOAT EPOXY PAINT C → UNDERCOAT EP 213 or 215 HB</p>
<p>Practical spreading rate : 1l/Sq.m/mm of thickness</p>		<p>SOLVENT FREE EPOXY FILLER B → MIX FILL 100 OPTION</p>
<ul style="list-style-type: none"> • 1 to 2 coats of 100 to 120 dry microns • Theoretical spreading rate : EP 213 HB : 4,8 Sq.m/L for 120 dry microns EP 215 HB : 4,2 Sq.m/L for 120 dry microns 	<p>EP 213 or 215 HB</p>	<p>UNDERCOAT EPOXY PAINT C → UNDERCOAT EP 213 or 215 HB</p>
<ul style="list-style-type: none"> • 1 coat of 60 to 70 dry microns • Theoretical spreading rate : 7,4 Sq.m/L for 70 dry microns 	<p>PU 77</p>	<p>POLYURETHANE ACRYLIC LACQUER D → ACRYLTOP PU 77 Color RAL or AFNOR Roller or AIRLESS application</p>

* ALL OUR INFORMATION IS INDICATIVE AND NONCONTRACTUAL